

10 PACK O-RING EPDM 5.3 x 2.4

ART. NO. 400830E

GENERAL



KEOFITT has the widest selection of spare parts and accessories to complete your sampling system.



O-ring is included in parts & accessories - contact KEOFIT for further details.



CERTIFICATION*

- EU EC 1935/2004 · EU EC 2023/2006 · DK No.822 06/2013 · FDA CFR 21 §177.2600 · USP Class VI
- REACH · RoHS · ADI Free · Keofitt DoC

TECHNICAL DATA

Type:	EPDM, Light Grey (402)
Hardness, ASTM D2240 [Shore A]:	75.00
Tensile strength, ASTM D412 [MPa]:	11.00
Ultimate Elongation, ASTM D412 [%]:	585.00
Compression Set, Method B 22 hours at 150°C / 302 °F, ASTM D395 [%]:	25
Temperature Resistance [°C/°F]	-40 - +150 / -40 - +302
Heat Resistance 70h at 150 °C / 302 °F, ASTM D865:	
- Change in Hardness [Shore A]:	2.80
- Change in Tensile strength [%]:	12.00
- Change in Ultimate Elongation [%]:	-25.00
Net weight [kg/lbs]:	0.0002 kg / 0.0004 lbs
Storage stability, ISO 2230	

*For further information and download please visit www.keofitt.dk